

DENNISON STANDARD TEST WAXES

30-17



FOR DETERMINING THE RESISTANCE TO SURFACE PICK OF PAPER AND BOARD

Dennison type Wax Pick Testing is for the evaluation of surface strength on paper and paperboard. Waxes are heated and applied to the surface of the sheet. After cooling, they are pulled from the surface and the wax stick is checked to see if it has pulled fiber or coating from the surface. The highest value wax which does not rupture the surface is reported as the pick strength of the sheet.

This traditional test has been used for many years and is well known in all parts of the world. It is simple, easy to use, and inexpensive.

Applicable standards: TAPPI T459
For testing in accordance with TAPPI method T-459



APPLICATION

The integrity of a paper or board surface depends both on the characteristics of the fibre matrix and those of the applied coating. The fibres must be as evenly distributed as possible, be "keyed" into the sheet with sufficient bonding to adjacent fibres and have liquid absorption properties to give the correct "bleed" into the sheet of the coating adhesive or binder and the water dispersant.

The coating must have the correct ratio of pigment and binder to correlate both with the base paper quality to ensure strong adhesion, also to give the desired "finish" to the product. The degree of adhesion and hence surface integrity maintained under conditions imposed by subsequent drying, calendaring and printing operations is widely measured with Dennison waxes.

TEST DESCRIPTION

The Dennison wax set consists of a series of hard resin, non-oily waxes with graded degrees of adhesion. Each of the waxes in the series has a cross section of 18 x 18 mm and is identified by code. In operation, the appropriate wax is softened over a spirit lamp and pressed onto the test piece held in place with a hollow wooden block. After cooling, the wax is pulled vertically from the sheet and the surfaces inspected. The test is repeated using the waxes in numerical order until the sample surface blisters, breaks, picks or lifts. The samples may be graded in terms of the "critical wax strength numbers" which is the highest number of wax stick that does not disturb the surface of the sample.

ORDERING INFORMATION

Part Number 30-17-00-0001 (full test kit)

Dennison Standard Paper Testing Wax Kit comprising one stick of each wax type 2A through 23A, plus one extra 8A wax stick (18 wax sticks total in kit), with an alcohol lamp, one wick, and wooden pull block.

Part Number: 30-17 with wax stick number (ex. 30-17-02, 30-17-20)

Replacement waxes are sold by the box, 8 waxes of a particular value per box.

Following numbers are available: (please list when ordering replacements, 8 waxes per box of the same value)
2A, 3A, 4A, 5A, 6A, 7A, 8A, 9A, 10A, 11A, 12A, 13A, 14A, 16A, 18A, 20A, 23A

DIMENSIONS AND WEIGHTS:

Dimensions (WxDxH): 350 x 150 x 80 mm (13.7 x 5.9 x 3.1 in)

Box for Transport (WxDxH): 410 x 300 x 250 mm (16.1 x 11.8 x 9.8 in)

Weight net/gross: 3 kg / 4 kg (6.6 / 8.8 lb)

Main Headquarters

Testing Machines Inc.
40 McCullough Drive
New Castle, DE 19720
Tel: (302) 613-5600
Fax: (302) 613-5619
Info@testingmachines.com

Büchel BV
t/a Messmer Büchel
Fokkerstraat 24, 3905 KV
Veenendaal, Netherlands
Tel: +31 (0)318 521500
Fax: +31 (0)318 540358

Lako Tool and Manufacturing Inc.
7400 Ponderosa Road
Perrysburg, Ohio 43552
Tel: (419) 662-5256
Fax: (419) 662-8225

Lawson Hemphill
1658 G A R Highway
Swansea, MA 02777
Tel: (508) 679-5364
Fax: (508) 679-5396
Information@
lawsonhemphill.com

Adamel Lhomargy SARL
Z.A. de l'Habitat, Bâtiment 6
Route d'Ozoir, 77680
Roissy en Brie, France
Tel: +33 (0) 1 64402910
Fax: +33 (0) 1 64409211

TMI Canada
40 McCullough Drive
New Castle, DE 19720
Tel: (302) 613-5600
Fax: (302) 613-5619
canada@testingmachines.com



www.testingmachines.com

www.lakotool.com

www.lawsonhemphill.com